

P84 & PTFE composited felt		
Fiber		P84 & PTFE staple fiber
Scrim		PTFE filament yarn
Weight (gsm)		650
Thickness (mm)±0.1		1.4
Width (m)		≤2.2
Air permeability (l/dm ² /min@200pa)		20-35
Tensile strength (N/5×20cm)	Warp	≥850
	Weft	≥900
Tensile elongation(%)	Warp	≤10
	weft	≤15
Temperature (°C)	Continue	240
	Instant	260
Finish treatment		Calendering, Heat setting, PTFE impregnation PTFE membrane
Anti-acid		Excellent
Anti-alkali		Excellent
Anti-abrasion		Good
Hydrolysis stability		Excellent